



STC SAFETY & SECURITY FILMS

SAFETY	VISUAL LIGHT TRANSMITTED (VLT)	TENSILE STRENGTH AT BREAK	ELONGATION AT BREAK	BREAK STRENGTH LB/INCH	UV REJECTED 380NM	THICKNESS	PLY
SF 4	88	33993	145%	113	99%	4mil	1
SF 8	88	32578	146%	167	99%	8mil	1
SF 12	84	31674	145%	288	99%	12mil	3
SAFETY + SKIN AND EYE CARE	VISUAL LIGHT TRANSMITTED (VLT)	TOTAL SOLAR ENERGY REJECTED (TSER)	TENSILE STRENGTH AT BREAK	ELONGATION AT BREAK	BREAK STRENGTH LB/INCH	UV REJECTED 400nm	THICKNESS
SCF SF 5/70	69	54	33993	145%	124	99.5%	5mil

Note:

This information is the best currently available on the subject. The result should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of the supplier's effort to improve the quality or production efficiency